



****ALL LIGHT POLE BASES ARE CUSTOM, & ARE NON-RETURNABLE****

SPECIFICATIONS :

- CONCRETE MINIMUM COMPRESSIVE STRENGTH - 4,000 PSI @ 28 DAYS.
- CONCRETE AIR ENTRAINMENT : 4% - 9%.
- TYPE I , OR TYPE III CEMENT.
- STEEL REINFORCEMENT:
 - #3 DEFORMED VERTICAL BAR (GR. 40) ASTM A-615.
 - #4 DEFORMED BAR HORIZONTAL HOOPS @ 12" O.C., (GR.60) ASTM A-615
- APPROXIMATE WEIGHT : 420 LBS/FT.
- ANCHOR BOLTS PROVIDE BY OTHERS.
- BOLT PATTERN PER LIGHT POLE MANUFACTURER SPECIFICATIONS.

Conduit Size :

Conduit Location (as Required) :
0,90,180,270 Degrees

Customer Acceptance (Signature)

Date

ENGINEERS REMARK :

NOTES :



EASTERN PRECAST
COMPANY , INCORPORATED

2 COMMERCE DRIVE, BROOKFIELD, CT 06804
PHONE : (203) 775 - 0230 FAX : (203) 740 - 2059
WWW.EASTERNPRECAST.COM

24" CONCRETE LIGHT POLE BASE

MATERIAL :

DOCUMENT APPROVED
BY : DATE :

DWNG DATE : 02/12/2018

CHKD DATE :

TOLERANCE

MODEL NO.

LOAD RATING

REVISION 1 - DATE

REVISION 2 - DATE

REV